## ADVISORY ON THE USE OF THIS DOCUMENT

The information contained in this document has been developed solely for the purpose of providing general guidance to employees of the Goddard Space Flight Center (GSFC). This document may be distributed outside GSFC only as a courtesy to other government agencies and contractors. Any distribution of this document, or application or use of the information contained Merein, is expressly conditioned upon, and is subject to, the following understandings and limitations:

- (a) The information was developed for general guidance only and is subject to change at any time;
- (b) The information was developed under unique GSFC laboratory conditions which may differ substantially from outside conditions;
- (c) GSFC does not warrant the accuracy of the information when applied or used under other than unique GSFC laboratory conditions;
- (d) The information should not be construed as a representation of product performance by either GSFC or the manufacturer;
- (e) Neither the United States government nor any person acting on behalf of the United States government assumes any liability resulting from the application or use of the information.

## Memorandum

PARAMAX A Unisys Compagy

DATE:

November 6, 1992

PPM-92-272

TO:

B. Fafaul/311

FROM:

K. Sahu

SUBJECT: Radiation Réport on FAST/MUE

Part No. 54AC169DMQB (54AC169)

cc:

R. Kolecki/740.4

T. Miccolis A. Sharma/311 Library/300.1 --L. Cusick/740.4

A radiation evaluation was performed on 54AC169 (Bidirectional Counter) to determine the total dose tolerance of these parts. brief summary of the test results is provided below. detailed information, refer to Tables I through IV and Figure 1.

The total dose testing was performed using a cobalt-60 gamma ray source. During the radiation testing, eight parts were irradiated under bias (see Figure 1 for bias configuration), and two parts were used as control samples. The total dose radiation steps were 5, 10, 20, 40 and 60 krads\*. After 60 krads, parts were annealed at +25°C for 168 hours. The irradiation was then continued to 100 krads and to 140 krads (cumulative). The dose rate was between 0.15 and 2.2 krads/hour, depending on the total dose level (see Table II for radiation schedule). After each radiation exposure and annealing treatment, parts were electrically tested according to the test conditions and the specification limits\*\* listed in Table III. These tests included five functional tests (three at 1.0MHz with VCC = 3.0V, 4.5V, and 5.5V and two at 10.0 MHz with VCC = 3.3V and 5.0V).

All ten parts passed initial (pre-rad) electrical tests. eight irradiated parts passed all electrical tests up to and including the 40-krad irradiation. After the 60-krad irradiation, two parts (SN 253 and 255) exceeded the maximum specification limits of 160 uA for ICCL and ICCH with readings of 516 and 575 uA, respectively, for SN 255 and 185 and 231 uA for SN 253. However, after annealing for 168 hours at 250C, only one part (SN 255) exceeded the limits for ICCL and ICCH, with readings of 267 and 301 uA, respectively. After irradiation to 100 and 140 krads, four parts (SN 253, 255, 257 and 258) exceeded the limits for ICCL and ICCH with readings (after 140 krads) varying from 2.0 to 6.8 mA.

<sup>\*</sup>The term rads, as used in this document, means rads(silicon). \*\*These are manufacturers' non-irradiated data specification limits. No post-irradiation limits were provided by the manufacturer at the time these tests were performed.

After a final annealing at 100°C, none of the parts exhibited any rebound effect.

All parts passed the five functional tests throughout all irradiation and annealing steps.

Table IV provides a summary of the functional test results, as well as the mean and standard deviation values for each parameter after different irradiation exposures and annealing steps.

Any further details about this evaluation can be obtained upon request. If you have any questions, please call me at (301) 731-8954.

## ADVISORY ON THE USE OF THIS DOCUMENT

The information contained in this document has been developed solely for the purpose of providing general guidance to employees of the Goddard Space Flight Center (GSFC). This document may be distributed outside GSFC only as a courtesy to other government agencies and contractors. Any distribution of this document, or application or use of the information contained herein, is expressly conditional upon, and is subject to, the following understandings and limitations:

- (a) The information was developed for general guidance only and is subject to change at any time;
- (b) The information was developed under unique GSFC laboratory conditions which may differ substantially from outside conditions;
- (c) GSFC does not warrant the accuracy of the information when applied or used under other than unique GSFC laboratory conditions;
- (d) The information should not be construed as a representation of product performance by either GSFC or the manufacturer;
- (e) Neither the United States government nor any person acting on behalf of the United States government assumes any liability resulting from the application or use of the information.

TABLE I. Part Information

Generic Part Number:

54AC169

Part Number:

54AC169DMQB

FAST/MUE

Control Number:

6306

Charge Number:

C24017

Manufacturer:

National Semiconductor Corp.

Lot Date Code:

9228A

Quantity Tested:

10

Serial Numbers of Radiation Samples:

252, 253, 254, 255, 256, 257, 258, 259

Serial Numbers of Control Samples:

250, 251

Part Function:

Bidirectional Counter

Part Technology:

CMOS

Package Style:

16-pin DIP

Test Engineer:

K. Kim

TABLE II. Radiation Schedule for 54AC169

EVENTS	DATE
1) Initial Electrical Measurements	10/07/92
2) 5 KRAD IRRADIATION (0.28 krads/hour)	10/07/92
POST-5 KRAD ELECTRICAL MEASUREMENT	10/08/92
3) 10 KRAD IRRADIATION (0.26 krads/hour)	10/08/92
POST-10 KRAD ELECTRICAL MEASUREMENT	10/09/92
4) 20 KRAD IRRADIATION (0.15-0.24 krads/hour*)	10/09/92
POST-20 KRAD ELECTRICAL MEASUREMENT	10/14/92
5) 40 KRAD IRRADIATION (1.18 KRADS/HOUR)	10/15/92
POST-40 KRAD ELECTRICAL MEASUREMENT	10/16/92
6) 60 KRAD IRRADIATION (1.25 KRADS/HOUR)	10/16/92
POST-60 KRAD ELECTRICAL MEASUREMENT	10/19/92
7) 168 HOUR ANNEALING @25°C	10/19/92
POST-168 HOUR ANNEAL ELECTRICAL MEASUREMENT	10/26/92
8) 100 KRAD IRRADIATION (2.1 KRADS/HOUR)	10/26/92
POST-100 KRAD ELECTRICAL MEASUREMENT	10/27/92
9) 140 KRAD IRRADIATION (2.22 KRADS/HOUR**)	10/27/92
POST-100 KRAD ELECTRICAL MEASUREMENT	10/28/92
10) 168 HOUR ANNEALING @100°C*** POST-168 HOUR ANNEAL ELECTRICAL MEASUREMENT	10/29/92 11/05/92

ALL ELECTRICAL MEASUREMENTS WERE PERFORMED AT 25°C.

PARTS WERE IRRADIATED AND ANNEALED UNDER BIAS; SEE FIGURE 1.

\*Due to a power outage, irradiation stopped after 20 hrs. at .15 krads/hr. After 37 hrs. of annealing at 25°C, irradiation resumed for 23 hrs. at .24 krads/hr.

\*\*The originally scheduled step was the  $100\,^{\circ}\text{C}$  annealing at this point. However, the parts erroneously received an additional  $40\,^{\circ}$ krads of radiation exposure.

\*\*\*High temperature annealing is performed to accelerate long term time dependent effects (TDE), namely, the "rebound" effect due to the growth of interface states after the radiation exposure. For more information on the need to perform this test, refer to MIL-STD-883D, Method 1019, Para. 3.10.1.

Table III. Electrical Characteristics of 54AC169

PART NU ;	54ACT SYUNGB   PART TYPE : 4-	STAGE SYNCHRONOUS BIDIRECTIONAL UNTER (16-PIN DIP).
	EDCATION	TEST SPECIFICATIONS
DISK LABEL Directury	: SI10577A : LIB 25 : DUAT:EPRUGRAMS.577] NA	TIONAL SEMI. DATABOOK 1990
	TESTS PERFORM	50
PARAMETER ###################################	VCC VIL VIH CONDITIONS  ===	PINS LIMITS a-550 TO +1250 ALL I/O VOL<1.50V , VOH>1.50V ALL I/O VOL<2.25V , VGH>2.25V ALL I/O VOL<2.75V , VOH>2.75V ALL I/O VOL<1.50V , VOH>1.50V ALL I/O VOL<1.50V , VOH>2.75V
	DC PARAMETRIC TEST	
**************************************	VCC VIE VIM CONDITIONS  3.0V 0.90V 2.10V LOAD = -50UA 4.5V 1.35V 3.15V LOAD = -50UA 5.5V 1.05V 3.55V LOAD = -120UA 4.5V 1.35V 3.15V LOAD = -120UA 4.5V 1.35V 3.15V LOAD = -24MA 5.5V 1.05V 3.35V LOAD = -24MA 5.5V 1.05V 3.35V LOAD = -50MA	OUTS
VOL1 VOL2 VOL3 VOL3 VOL3 VOL3 VOL3	VCC VIL VIH CONDITIONS 3.UV 0.90V 2.10V LOAD = +50UA 4.5V 1.35V 3.15V LOAD = +50UA 5.5V 1.65V 3.85V LOAD = +12NA 4.5V 1.35V 3.15V LOAD = +24MA 5.5V 1.65V 3.85V LOAD = +24MA 5.5V 1.65V 3.85V LOAD = +50MA	PINS LIMIT\$ \$-550 TO #1250 ===== ==============================
114		PINS LIMITS 2-55C TO +125C =====
ICUH		PINS LIMITS 8-550 TO +1250

Table III (cont.). Electrical Characteristics of 54AC169

!					
	. 40/Nu-40_AC	1EST3.	PERFORMED O	URING FUNCTION	IAL TEST #4
PARAMETER	VCC VIL	VIH #==	AREQUENCY	7277 223	HITS AT -550 TO +1250
1 Ts (Pn) 1 Th (Pn)	3.3V U.JV	¥.3V	10.0 MHz	Pn -> CP CP -> Pn	
! Ta (CEP_)	3.34 0.0V	3.3V 3.3V	10.0 MHz 10.0 MHz	CP -> CP CP -> CEP	>13.5ns (Min.) > 0.5ns (Min.)
Ts (Cat_)	3.34 0.07	3.3V 3.3V	10.0 MHz 10.0 MHz	CET_=> CP CP => CET_	>13.5mS (Min.) > 0.5mS (Min.)
Ta (Pc_) Tn (Pc_)	3.3V 0.0V	۸۲۰۲ ۸۲۰۲	10.0 MHz N 10.0 MHz	PE> CP CP> PE_	> 8.5n\$ (Min.) > 0.5n\$ (Min.)
Ta (UD_) Th (UD_)	3.3V 0.0V 5.3V 0.0V	3.3V 3.3V	10.0 MHz 10.0 MHz	UD_~> CP CP -> UD_	>13.0n5 (Min.) > 0.5n5 (Min.)
Tar (CP)	3.3v 0.0V	٧٤٠٤	10.0 MHz	G P	> 5.0nS (Hin)
	GU/MD-GO AC	LEZIZ	PERFORMED D	URING FUNCTION	AL TEST #5
PARAMOTER	ACC AIF	VIH	FREDOEMCA	PINS LI	MITS AT -55C TO +125C
i is LPnJ	5.0V 0.0V		10.0 MHz 10.0 MHz	Pn => CP CP => Pn	> 4.5ns (Min.) > 2.5ns (Min.)
.Ta (CcP_)					
I Th (CEP_)	5.0V 0.0V 5.0V 0.0V	5.0V V∪.č	10.0 89z 10.0 86z		> 9.005 (Min.) > 2.505 (Min.)
! Tn (CEP_) ! ! Ts (CET )	5.00 0.00	3.0V			> 9.005 (Min.) > 2.505 (Min.) > 9.505 (Min.) > 2.505 (Min.)
! Tn (CEP_) ! ! Ts (CET )	5.0V 0.0V 5.0V 0.0V 5.0V 0.0V	5.0V	10.0 MHz	CET_=> CP CP => CET_	
Tn (CEP_)    Ts (CET_)   Tn (CET_)   Tn (Pc_)	5.0V 0.0V 5.0V 0.0V 5.0V 0.0V 5.0V 0.0V	5.0V 5.0V 5.0V	10.0 MHz 10.0 MHz 10.0 MHz 10.0 MHz	CET_=> CP CP -> CET_	> 9.5n5 (Min.) > 2.5n5 (Min.) > 6.5n5 (Min.) > 2.un5 (Min.)

AC PARAMETRIC TESTS PERFO	RMED
PARAMETER VCC VIL VIM FREQUENCY PINS	LIMITS AT -550 TO +1250
i TPRLT (PE=0) \5.0V 0.0V 5.0V 1.0 MHz CP to 0	n > 1.0ns > < 13.0ns
TPLH2	n > 1.0ns / < 12.0ns n > 1.0ns / < 13.0ns
TPLMS 5.00 0.00 5.00 1.0 MMz CP to T TPHCS 5.00 0.00 5.00 1.0 MMz CP to T	
TPLH4 5.0V 0.0V 5.0V 1.0 MHz CET_ to TPHL4 5.0V 0.0V 5.0V 1.0 MHz CET_ to	
TPLH5 5.0V U.OV 5.0V 1.0 MHz UD to TPHL5 5.0V U.OV 5.0V 1.0 MHz UD to	TG > 1.0ns / < 13.0ns TG > 1.0ns / < 12.0ns
COMMENTS/EXCEPTIONS	
(3) VIH and VIL are tested during VDH and VOL t	ests as GO/NO-GO tests.
(4) IDDH and 10DL are tested during VOH7 and VO	L7 tests as GO/NU-GO tests.
(5) GO/NU-GD AC tests are performed during FUNT	IONAL test#'s 4 and 5.
(4) AC parametric tests at VCC = 3.3V is NOT pe	rformed.
(5) This program detacts improper DUT insertion	·
HARDWARE REQUIREMENTS	TEST TEMPERATURES
OEVICE CONFIGURATION : 15-PIN DIP S-5J LUAD BUARD # 17 : DUT pin#8 jumped to GND.	+25 DEG. C.  x  +55 DEG. G.  x  +125 OEG. C.  x
PROGRAMMER : K. Kim	; DATE : 09-17-92

TABLE IV: Summary of Electrical Measurements After Total Dose Exposures and Annealing for 54AC169 1/

•			$\overline{}$				rotal	Doss	Evno	20170	(TDE	·	rads		1		,		,, <u> </u>	<del>.</del> .		
			T A	1-1	Π,							<del></del>	Tade	<u>'</u>	Ani	<u>neal</u>	<u> </u>	TDE	(krada	;)	Ann-	eal_
	Spec	Lim./2	Init	ıaı	;	5	-	10	:	20	4	€0		6 <b>0</b>	168	hrs	10	0.0	140	1/4	168	hrs.
Parameters		max			L	- 4		_			1		:		@2:	5°C					<b>@</b> 10	0°C
	Hz, 3.		mean	sd	mean	sđ	mean		mean		mean	sđ	mean		mean	sd	mean	sd	mean	sd	mean	sd
<del></del>			PASS		PASS		PASS		PASS		PASS		PASS		PASS		PASS		PASS		PASS	
	Hz, 4.		PASS		PASS		PASS	_	PASS		PASS		PASS		PASS		PASS	-	PASS	_	PASS	
	Hz, 5.		PASS		PASS		PASS		PASS	<u> </u>	PASS		PASS		PASS		PASS		PASS		PASS	<u> </u>
	MHz,3.		PASS		PASS		PASS		PASS		PASS		PASS		PASS		PASS		PASS		PASS	
	MHz,5.0		PASS		PASS		PASS		PASS		PASS		PASS		PASS		PASS		PASS		PASS	<del></del> -
VOH1 /3 V		3.0	2.99	0	2.99	0	2.99	.01	2.99		2.99	.01	2.99		2.99	.01	2.99		2.99	.01	2.99	
AOH3 A		5.5	5.49	0	5.49	0	5.49	0	5.49	_	5.49	Ď	5.49		5.49	0	5.49		5.49	- 71	5.49	<u> </u>
VOH5 V		4.5	4.20	.02	4.20	.02	4.20	.02	4.20	_	₹.20	.02	4.20	.02	4.20		4.19		4.19	0.2		0
VOH7 V	3.85	5.5	4.94	.03	4.93	.03	4 94		4.94		4.93		4.93		<b>≠.9</b> 3		4.91		.2 1137 2774	.02	4.19	.02
VOL1 mV	0	100	0	0	0	0	0	0	0	0	0	0	0	0	6	-04	0		4.91	.04	4.92	.03
VOL7 mV	0	1650	518	54	520	93	428	34	489	52	592	90	489	96	420	32	***************	0	0	0	0	0
IIH nA	0	1000	0	0	0	0	C	0	0	0	0	-0	0	0	0		444	71	437	76	503	141
IIL nA	-1000	0	0	0	0	0	0	o -	0	<u> </u>	0	<del>_</del> 0	0	0	0	0	0	_ 0 _	0	<u> </u>	0	_ 0
ICCL uA	0	160	0	0	0.03	.07	4.98	_ <u>`</u> _	18.0	6.4	34.8	39	103	<u> </u>		_0_	0	0	0	0	0	0
ICCH uA	0	160	0	0	0.03		4.15		13.2		37.9	48	122		53.3	9.5			2005		13.8	8.6
TPLH1 ns	0	12.0	7.21	.17	7.15		7.16	_	7.23		7.13			<del></del> +	66.5	96			1832			1.4
TPHL1 ns	0	13.0	6.67		5.60		<b>6</b> .61		6.66				7.10		7.08		5.98		6.90		7,13	.16
TPLH2 ns		12.0	7.04		3 11 11 11 11		6.99		7.06	_		_	6.50		6.95	.13	5.88		6.79	<u>.12</u>	7.08	.15
TPHL2 ns	0		6.68		5.60		6.62		6,67	$\overline{}$			6.94		7.17	.28	7.08		7.04	.30	7.00	. 14
			1. T. F. J. J.		1-1-1-1-1-1-1-1-1-1-1-1-1-1-1-1-1-1-1-	, 20	(4.5. U.S.)	. 40	X > X 6	- 20	6.53	.25	6.50	.26	6.72	<u>. 33 j</u>	6.62	.32	6.52	<u>.3</u> 2	7.12	. 35


## Note:

1/ The mean and standard deviation values were calculated over the eight parts irradiated in this testing. The control samples remained constant throughout the testing and are not included in this table.

2/These are manufacturers' non-irradiated data sheet specification limits. No post-irradiation limits were provided by the manufacturer at the time the tests were performed. 3/ No significant variation was observed in VOH or VOL during irradiation and annealing. Additional data are available on request.

 $4/{
m The}$  originally scheduled step was the 100°C annealing at this point. However, the parts were irradiated to an additional 40 krads due to operator error.

Figure 1. Radiation Bias Circuit for 54AC169



Pin Names	Description
CEF	Count Enable Parallel Input
CET	Count Enable Tricklo Input
CP	Clock Pulse Input
Po-Pa	Parallel Data Inputs
PE	Parallel Enable Input
U/D	Up-Down Count Control Input
O <sub>0</sub> -Q <sub>3</sub>	Flip-Flop Outputs
₩C.	Terminal Count Output

	Mode Select Table									
PE	CEP	<u>ÇET</u>	U/0̄	Action on Rising Clock Edge						
L	×	×	Х	Load (P <sub>n</sub> to Q <sub>n</sub> )						
Н	Ł	L	H	Count Up (Increment)						
Н	Ĺ	L	L	Count Down (Decrement)						
н	н	Х	х	No Change (Hold)						
H	×	Н	×	No Change (Hold)						

NOTES)

) ALL REDISTOR VALUES R= 20 KR ±10% KIN

2) VCC = 5.0V ±05V VCC/2=25V ±025V 3) TEMPERATURE "+25°C AND +125°C (+8/0)